

# TOPSPEED

Ancillaries

12/03/2020

L1.08.04 UK &amp; Ireland

## DESCRIPTION

Special accelerator to increase the speed of drying and through hardening. Suitable for spot and panel repair.

For use in:


- 2K HS Extra Clear
- Topcoat HS 420

## 2K HS EXTRA CLEAR

Mixing ratio

2K HS Extra Clear

1-3 caps of Topspeed



## TOPCOAT HS 420


Mixing ratio

5 Topcoat HS 420

2 HS Hardener 420

1 Topspeed

Mixing stick N



## APPLICATION TECHNIQUE

Application

Apply the products as usual following recommendations in the relevant Technical Data Sheets.



# TOPSPEED

Ancillaries

12/03/2020

L1.08.04 UK &amp; Ireland

## Drying



|                   |               | 20°C    | 60°C   |
|-------------------|---------------|---------|--------|
| 2K HS Extra Clear | Dust dry      | 15 min  | 5 min  |
|                   | Dry to handle | 2.5 hrs | 12 min |
| Topcoat HS 420    | Dust dry      | 40 min  | 10 min |
|                   | Dry to handle | 6 hrs   | 20 min |

Product storage      Avoid extreme temperature fluctuation and high humidity levels

Shelf life              4 years at 20°C

**Akzo Nobel Coatings LTD**

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** 00 44 (0)1235 862226

## FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office  
Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.Lesonal.com](http://www.Lesonal.com)