

2K HS Extra Clear RTS











Clearcoats

08/11/2019

L1.05.06 UK & Ireland

DESCRIPTION

Two component, isocyanate hardening, quick drying clearcoat in aerosol.
 To be used for spot repairs up to panel repairs.
 The product is activated by pushing the red button on the pin at the bottom

Preparation		Shake well		Place button on pin at bottom		Push button once to activate
Application		Shake for 2 minutes		Distance 20-30 cm		2 coats
Flash-off		Before curing 5-10 minutes at 20°C				
		After use, invert aerosol to clear nozzle				
Drying			20°C	60°C		
			7 hrs	30 min		
Protection		Use suitable respiratory protection Akzo Nobel Car Refinishes recommends the use of fresh air supply respirator				

Read complete technical data sheet for detailed product information

2K HS Extra Clear RTS

Clearcoats

08/11/2019

L1.05.06 UK & Ireland

DESCRIPTION

Two component, isocyanate hardening, quick drying clearcoat in aerosol.
 To be used for spot repairs up to panel repairs.
 The product is activated by pushing the red button on the pin at the bottom

PRODUCT AND ADDITIVES

Product 2K HS Extra Clear RTS

Chemical Basis	2K HS Extra Clear RTS Hardener (integrated in canister)	Acrylic resins Poly-isocyanates
----------------	--	------------------------------------

METHOD OF USE

Substrates Lesonal Basecoat WB
 Lesonal Basecoat WB GT

APPLICATION TECHNIQUE

Product activation Activate product by pushing the red button on the pin at the bottom of the aerosol.
 Shake for at least 2 minutes before use. After use, invert aerosol to clear nozzle.

Application Apply two single coats.
 Allow a flash off time of 5 to 10 minutes.



Potlife 8 hours at 20°C
 (Potlife can be extended by storage in a cool environment)

Drying 		20°C	60°C
	Dust free	20 min	5 min
	Dry to handle	7 hrs	30 min

Layer thickness 50 – 60 microns

2K HS Extra Clear RTS

Clearcoats

08/11/2019

L1.05.06 UK & Ireland

Product storage	Avoid extreme temperature fluctuation and high humidity levels
-----------------	--

Shelf life	1 year at 20°C
------------	----------------

VOC	2004/42/IB(e)(840)640 The EU limit value for this product (product category : IIB.e) in ready to use form is max. 840 g/l VOC. The VOC content of this product in ready to use form is max. 640 g/litre.
-----	--

Akzo Nobel Coatings LTD

Address: Unit 2B, Didcot Park
Churchward, Southmead Industrial Estate
Didcot, Oxfordshire, OX11 7HB
Tel: 00 44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give, or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office
Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.Lesonal.com