

1K Multi Plastic Primer RTS








Adhesion Primers

06/11/2019

L2.01.06 UK & Ireland

DESCRIPTION

Air drying, one-pack primer to promote the adhesion on plastic car-body parts.

		Shake thoroughly before use	
Application distance		Approx. 20-30 cm	
Application		1 x 1 coat	
Flash-off		Recoatable after 20 minutes at 20°C	Recoatable within 24 hours at 20°C
		After use, invert aerosol to clear nozzle	
Recoatibility		All Lesonal primers, fillers and topcoats	
Protection		Use suitable respiratory protection Akzo Nobel Car Refinishes recommends the use of fresh air supply respirator	

Read complete technical data sheet for detailed product information

1K Multi Plastic Primer RTS

Adhesion Primers

06/11/2019

L2.01.06 UK & Ireland

DESCRIPTION

Air drying, one-pack primer to promote the adhesion on plastic car-body parts.

PRODUCT AND ADDITIVES

Product 1K Multi Plastic Primer RTS

Chemical Basis 1K Multi Plastic Primer RTS Polyolefin resin


METHOD OF USE

Substrates All plastic car parts with the exception of pure PE (polyethylene).

Substrate preparation Clean substrate (without OEM primer) with warm water and detergent.
 Degrease with Lesonal Degreaser.
 Scuff surface with Scotch Brite S (Grey) very fine.
 Degrease with Lesonal Degreaser and tack rag.

Mixing ratio

100 1K Multi Plastic Primer



APPLICATION TECHNIQUE

Application



Apply one even closed coat.

Minimum application temperature: 15°C



After use, invert aerosol to clear nozzle

1K Multi Plastic Primer RTS

Adhesion Primers

06/11/2019

L2.01.06 UK & Ireland

Drying



Recoat after
20 minutes at 20°C

Recoat within
24 hours at 20°C

Layer thickness 1 – 4 microns

Recoatibility All Lesonal primers, fillers and topcoats

Product storage Avoid extreme temperature fluctuation and high humidity levels

Shelf life 2 years at 20°C

VOC 2004/42/IIIB(e)(840)720
The EU limit value for this product (product category : IIB.e) in ready to use form is max. 840 g/l VOC.
The VOC content of this product in ready to use form is max. 720 g/litre.

Akzo Nobel Coatings LTD

Address: Unit 2B, Didcot Park
Churchward, Southmead Industrial Estate
Didcot, Oxfordshire, OX11 7HB
Tel: 00 44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office
Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.Lesonal.com