

# Plastic Parts

Technical Bulletin

09/11/2019

L8.06.03 UK &amp; Ireland

## DESCRIPTION

This document describes painting processes for exterior plastic car parts.

## PRIMER CHECK

**1. Check for OEM primer:** Sand the surface with sanding paper P500 grit. When the sanding paper reveals a powder, the plastic part is primed.


**2. Solvent sensitivity check:** Wet a cloth with Antistatic Degreaser SB and gently rub the primed part. When the primer dissolves, it is classified as sensitive.

## PREPARATION OF NON SENSITIVE PRIMED PLASTIC PARTS



Clean the surface with warm water and detergent, rinse sufficiently with clean water.


Next use Antistatic Degreaser SB.



Dry sand with P500 grit sanding paper.



Clean the surface using Antistatic Degreaser SB.



Apply the selected topcoat.  
See product TDS for detailed product information.

# Plastic Parts

Technical Bulletin

09/11/2019

L8.06.03 UK & Ireland

## PREPARATION OF SENSITIVE PRIMED PLASTIC PARTS



Clean the surface with warm water and detergent, rinse sufficiently with clean water.

Next use Degreaser WB.




Dry sand with P500 grit sanding paper.



Clean the surface using Degreaser WB.



Apply 1K Primer WB according TDS L2.07.01.



Apply the selected topcoat.  
See product TDS for detailed product information.


# Plastic Parts

Technical Bulletin

09/11/2019

L8.06.03 UK & Ireland


## UNTREATED PLASTIC PARTS



Heat the plastic car part for 20 minutes at 60°C




While the car part is still warm, clean the surface with warm water and detergent, rinse sufficiently with clean water.




Thoroughly abrade with a liquid abrasive in combination with water.  
 For hard plastics: Use a 3M VFN (Purple) abrasive pad.  
 For flexible / soft plastics: Use a 3M UFN (Grey) abrasive pad.  
 Rinse sufficiently with clean water.



Clean the surface using Antistatic Degreaser SB.



Allow for a minimum flash off time of 15 minutes at 20°C



Apply an adhesion primer:  
 1K Multi Plastic Primer                      TDS L2.01.05 / L2.01.06  
 2K Universal Plastic Primer                TDS L2.05.02

# Plastic Parts

Technical Bulletin

09/11/2019

L8.06.03 UK &amp; Ireland

## PLASTICIZING FILLERS AND TOPCOATS

Fillers "sanding"	Plasticizer/Additive	Hard	Flexible	Soft
2K HS Primer Filler	Flexible Additive	-	4:1	2:1
2K Filler 540		-	4:1	2:1
2K High Build Filler		-	4:1	2:1
2K Graphite Filler		-	4:1	2:1

Fillers "non sanding"	Plasticizer/Additive			
2K Filler 540	Flexible Additive	-	4:1	2:1
2K Graphite Filler		-	4:1	2:1

Topcoat	Plasticizer/Additive	Hard	Flexible	Soft
2K Topcoat HS420	Flexible Additive	-	-	-
2K HS Extra Clear		-	4:1	2:1
2K HS Fast Clear 420		-	-	-
2K HS Premium Clear 420		-	-	-

### Akzo Nobel Coatings LTD

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** 00 44 (0)1235 862226

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give, or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

#### Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.Lesonal.com](http://www.Lesonal.com)